




HAR 2120

RESORCINOL DIGLYCIDYL ETHER

DIFUNCTIONAL Aromatic



Typical Properties

Appearance	Pale Yellow Liquid
Viscosity @ 25°C	500 – 1,000 cps
Epoxy Equivalent Weight	120 – 130 g/eq
Hydrolyzable Chloride Content	< 0.1 %
Residual Epichlorhydrin	< 20 ppm

Advantages

- Very Low Viscosity Di-functional Aromatic
- Fast Curing with Most Hardeners
- High Cross Link Density
- Excellent Chemical Resistance to Acids (including concentrated sulfuric), Caustics and Solvents (including MeCl₂)
- Enhances Hardness, Compression Strength
- Improves Thermal Stability

Applications

- Corrosion Resistant Coatings and Adhesives
- Composite Pipe, Flanges and Fittings
- Versatile Adhesives including Polar and Porous Surfaces